

iQ EMINENT

TECHNICAL DATA

CERTIFICATION & CLASSIFICATION	STANDARDS	iQ Eminent
Type of floor covering	EN 14565	Homogeneous single layered vinyl flooring
Binder content	ISO 10581	Type I
CE certification	EN 14041	Yes
Classification	ISO 10874	Commercial: 34 Industrial: 43

TECHNICAL CHARACTERISTICS	STANDARDS	iQ Eminent
iQ surface treatment		Yes
Total thickness	ISO 24346	2.0 mm
Total weight	ISO 23997	2800 g/m ²
Form of delivery	ISO 24341 Sheet (rolls)	Approx. 23 lm x 200 cm Art. no. 21030_ _ _ 3 digit colour colour number

	STANDARDS	iQ Eminent
Dimensional stability	ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles
Reaction to fire	AS/ISO 9239.1 AS/NZ 3837 (wall)	Critical radiant flux ≥ 11.0kW/m ² Smoke 117%.min Group 3 238.8 m ² /kg
Residual indentation	ISO 24343-1	Required value: ≤ 0.10 mm Best measured value: 0.02 mm
Castor c	ISO 4918	Suitable
Ease of decontamination	ISO 8690	Excellent
Static electrical discharge	EN 1815	< 2 kV
Clean room	ISO 14644-1 ISO ASTM F24 F51	ISO class 4 Class A
Total VOC emissions	AgBB/DIBt Indoor air quality FloorScore RTS emission class	≤ 10 µg/m ³ (after 28 days) Platinum SCS certified M1
Underfloor heating		Suitable – max 27°C
Thermal resistance	EN 12667	Approx. 0.01 m ² K/W
Light fastness	EN ISO 105-B02	≥ level 6
Chemical resistance	ISO 26987	Excellent
Bacteria resistance	EN ISO 846:Part C	Does not favour growth
Slip resistance	DIN 51130 AS 4586	R10 P4
Wet room approval	N 13553 Annex A GBR approval system	Watertight Certified
Abrasion	EN 660:Part 2	≤ 2.0 mm ³
Flexibility	ISO 24344	Pass
Seam strength	EN 684	Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
Colours		34

The above information is subject to modification for the benefit of further improvement. (03/22).

CUSTOMS TARIFF : 482050000000F

Tarkett's instructions regarding installation, cleaning and maintenance should be observed.
Please contact Tarkett at the address shown for these instructions.



For Global Green Tag certificates please see the Tarkett Australia page at globalgreentag.com

According to European Classification ISO 10874 - EN 685

