























Technische tabel

Step voldoet aan de eisen van EN - ISO 10582 & EN 13845

		Surestep Original Surestep Star	Surestep Wood Surestep Stone Surestep Mineral Surestep Texture	Safestep R11	Safestep R12	Safestep Aqua	Surestep Laguna	
	Totale dikte	EN - ISO 24346	2,0 mm	2,0 mm	2,0 mm	2,0 mm	2,0 mm	
	Dikte slijtlaag	EN - ISO 24340	0,7 mm	0,7 mm	0,7 mm	0,7 mm	0,7 mm	
	Commercieel gebruik	EN - ISO 10874	Klasse 34	Klasse 34	Klasse 34	Klasse 34	Klasse 34	
	Industrieel gebruik	EN - ISO 10874	Klasse 43	Klasse 43	Klasse 43	Klasse 43	Klasse 43	
	Collectie		24 - 13	12 - 8 - 5 - 5	8	4	12	
	Rollbreedte	EN - ISO 24341	2,00 m	2,00 m	2,00 m	2,00 m	2,00 m	
	Rollengte	EN - ISO 24341	20 - 27 m	20 - 27 m	20 - 27 m	20 - 27 m	20 - 27 m	
	Totaalgewicht	EN - ISO 23997	2,75 kg/m ²	2,75 kg/m ²	2,75 kg/m ²	2,75 kg/m ²	2,75 kg/m ²	
	Dimensiestabiliteit	EN - ISO 23999	< 0,1%	< 0,1%	< 0,1%	< 0,1%	< 0,1%	
	Indrukbestendigheid	EN - ISO 24343-1	≤ 0,05 mm	≤ 0,05 mm	≤ 0,05 mm	≤ 0,05 mm	≤ 0,05 mm	
	Geschikt voor bureaustoelen	EN 425	Geschikt	Geschikt	Geschikt	Geschikt	Geschikt	
	Gebruik in natte omgeving	EN 13533	Ja	Nee	Ja	Ja	Ja	
	Kleurechtheid	EN - ISO 105 B-02	≥6	≥6	≥6	≥6	≥6	
	Flexibiliteit	EN - ISO 24344	ø 10mm	ø 10mm	ø 10mm	ø 10mm	ø 10mm	
		DIN 51130	R10	R10	R11	R12	R10	
	Slipweerstand	EN 13845 Annex D 50.000 omwentelingen <10% verlies	Klasse 34/43	Klasse 34/43	Klasse 34/43	Klasse 34/43	Klasse 34/43	
		EN 13845 Annex C	ESf	ESf	ESf	ESb	ESb / ESf	
		Din 51097				Klasse C	Klasse B	
	Weerstand tegen huishoudelijke chemicaliën	EN-ISO 26987	Goed	Goed	Goed	Goed	Goed	
	Elektrische weerstand	EN 1081 (R1)	> 1,10 ⁹ Ω	> 1,10 ⁹ Ω	> 1,10 ⁹ Ω	> 1,10 ⁹ Ω	> 1,10 ⁹ Ω	
Step voldoet aan de eisen van of EN 14041							 0200101-DeP-306	
	Brandgedrag	EN 13501-1	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1	
	Statische elektriciteit	EN 1815	< 2kV	< 2kV	< 2kV	< 2kV	< 2kV	
	Warmtegeleidingcoëfficiënt	EN 12524	0,25 W/m,K	0,25 W/mK	0,25 W/mK	0,25 W/mK	0,25 W/mK	
	Slipweerstand	EN 13893	DS: ≥0,30	DS: ≥0,30	DS: ≥0,30	DS: ≥0,30	DS: ≥0,30	